

请查收推荐的阻尼浆料配方。由于我们没有做过屋顶减噪的浆料。这个配方是基于汽车用浆料调整而来的。客户可以根据他们要求删减某些组分。

Produce date: 20230908

Operator:

Product name:

LASD-Coating 4569

Lot number:

Batch weight:

300

g

Formula:

	Name:	SC(%)	Recipe	Lot Number	Weight	Solid	Remark
1	Acronal 4569	50	28.00		84.00	42.00	
2	Dipropylene glycol	0	4.00		12.00	0.00	
3	Dehydran SE 2	19	0.10		0.30	0.06	
4	Dispex AA4140	45	0.50		1.50	0.68	
5	Dispex CX4230	28	0.15		0.45	0.13	
6	Xfast 0066	100	0.25		0.75	0.75	
7	CaCO <sub>3</sub> 325mesh	100	51.00		153.00	153.00	
8	Mica 325mesh	100	10.00		30.00	30.00	
9	Rheovis AS 1125	12.5	1.50		4.50	0.56	
10	Water	0	4.50		0.00	0.00	
	Subtotal		100.00		286.50	79.29%	