# Efka<sup>®</sup> FL 3776

general	slip and leveling agent Efka <sup>®</sup> FL 3776 is a new levelling agent with better compatibility and defoaming property.	
	<ul> <li>improves leveling</li> <li>prevents cratering</li> <li>helps substrate wetting</li> <li>acts as a defoamer and de-aerated</li> <li>does not interfere with intercoat and the substrate wetting</li> </ul>	
chemical nature	fluorocarbon-modified polymer	
Properties		
physical form	clear, colorless liquid	
shelf life	The product should be stored in a cool dry place. When kept in its original unopened containers, it will keep up to 4 years.	
typical properties	active ingredients	~ 70%
(no supply specification)	solvent	xylene
	density at 20 °C (68 °F)	~ 0.98 g/cm <sup>3</sup>
	flash point	25 °C

## Application

Efka® FL 3776 is especially suitable for:

- baking enamels based on alkyd, acrylic or polyester resins
- polyurethane coatings
- two-pack epoxy coatings
- air-drying alkyd systems

### recommended concentrations

0.5-2.0% on total formulation

Efka® FL 3776 should be added at the end of the batch preparation.

#### Safety

When handling this product please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

#### Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product sexclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

 $^{\circledast}$  = registered trademark,  $^{\intercal M}$  = trademark of BASF Group, unless otherwise noted

BASF SE Formulation Additives 67056 Ludwigshafen, Germany www.dispersions-pigments.basf.com

formulation-additives-asia@basf.com