

Efka[®] PB 2720

(old : Efka[®] 2720)



general

defoamer

Efka[®] PB 2720 supports the quick de-aeration of thermosetting resin systems so that foam and blister-free self leveling compounds and laminates can be processed.

chemical nature

solution of defoaming substances, silicone free

Properties

physical form

colorless, clear to slightly hazy liquid

shelf life

The product should be stored in a cool dry place. When kept in its original unopened containers, it will keep up to 4 years.

typical properties (no supply specification)

solvent	alkyl benzene/ industrial spirit (boiling range 140–165 °C [284–329 °F])
density at 20 °C (68 °F)	~ 0.84 g/cm ³
refractive index	1.474
flash point	26 °C (79°F)

Application

Efka[®] PB 2720 can be used in pigmented or non-pigmented resin systems such as

- unsaturated polyesters (SMC/BMC gelcoats and synthetic mortars)
- two-pack epoxies
- PVC-compounds

If used in conjunction with Efka[®] FA 4644 in pigmented compounds, a lower viscosity results thereby aiding the air release properties.

recommended concentrations

0.1–1.0% on total formulation

Efka[®] PB 2720 should be incorporated by simple mixing. A homogeneous mix will increase the efficiency.

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of the BASF Group, unless otherwise noted

BASF SE
Formulation Additives
67056 Ludwigshafen, Germany
www.dispersions-pigments.basf.com
formulation-additives-asia@basf.com
formulation-additives-europe@basf.com
formulation-additives-nafta@basf.com
formulation-additives-south-america@basf.com