

# Efka<sup>®</sup> PX 4787

**Product description** Efka PX 4787 is a high molecular weight dispersing agent designed to disperse and stabilize organic pigments and carbon-blacks. Use of Efka PX 4787 results in significantly lower pigment paste viscosity without having to use high level of dispersant. Efka PX 4787 is suitable for industrial and automotive coatings, especially where resin-matrix reactive dispersant is desired.

- Key benefits**
- Exponentially lower pigment paste viscosity at lower addition levels
  - Relatively consistent and stable viscosity over wide addition range
  - Cross-linkable with -NCO and melamine-based resin matrices for optimal durability
  - Exceptional jetness for carbon black pigments
  - Excellent gloss development
  - Highest available transparency in CAB-containing systems

**Chemical nature** Polymer with pigment-affinic groups

## Properties

**Physical form** Brownish liquid

<b>Technical data</b> (not supply specification)	solvent	butyl acetate
	active ingredients	~ 70 %
	amine value	~ 15 mg KOH/g
	Viscosity	~ 1000 mPa.s

\* To comply with US EPA requirements currently, Efka PX 4787 is recommended for use in automotive coatings only in the US.

## Application

Efka PX 4787 is highly efficient dispersant for Resin-Free Pigment Concentrates (RFPC) to be used in a wide range of solvent-based industrial and automotive coatings.

Efka PX 4787 can also be used in single dispersant based direct grinding of pigments or as a part of Resin-Containing Pigment Concentrates (RCPC).

## Formulation guideline

An example formulation for resin-free pigment concentrates (RFPC):

The following starting point dry-over-dry addition levels, based on pigment loading, are recommended for pigment concentrates. For optimum results, a ladder study should be performed in the specific binder formulations.

inorganic pigments	10–15 % on oil absorption value
organic pigments (green, blue, violet)	15–30 % on BET value
organic pigments (yellow, orange, red)	15–45 % on BET value
carbon blacks (LCF)	15–20 % on DBP value
carbon blacks (HCC)	40–50 % on DBP value

## Storage

Efka® PX 4787 should be stored in a dry and cool place.

## Contacts worldwide

Asia  
 BASF East Asia Regional Headquarters Ltd  
 45/F, Jardine House  
 No. 1 Connaught Place  
 Central Hong Kong  
 China  
[formulation-additives-asia@basf.com](mailto:formulation-additives-asia@basf.com)

North America  
 BASF Corporation  
 11501 Steele Creek Road  
 Charlotte, NC 28273  
 USA  
[formulation-additives-nafta@basf.com](mailto:formulation-additives-nafta@basf.com)

Europe  
 BASF SE  
 Formulation Additives  
 67056 Ludwigshafen  
 Germany  
[formulation-additives-europe@basf.com](mailto:formulation-additives-europe@basf.com)

South America  
 BASF S.A  
 Rochaverá - Crystal Tower  
 Av. das Nações Unidas, 14.171  
 Morumbi - São Paulo-SP  
 Brazil  
[formulation-additives-south-america@basf.com](mailto:formulation-additives-south-america@basf.com)

## Validity

This Technical Data Sheet is valid for all versions of the OBEfka® PX 4787.

## Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

## Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark

™ = Trademark of the BASF Group, unless otherwise noted

[www.basf.com/formulation-additives](http://www.basf.com/formulation-additives)