

Rheovis® HS 1332

general

rheology modifier

- excellent mid- to high-shear thickener and rheology-control agent for aqueous coatings

chemical nature

hydrophobically modified acrylic swellable copolymer emulsion (HASE) in water

Properties

physical form

white liquid (dispersion)

storage

Rheovis® HS 1332 should be stored in a cool dry place.

typical properties (no supply specification)

solid content	~ 40 %
density at 20°C	~ 1.079 g/cm ³
Brookfield viscosity at 25°C, 20 rpm	~ 5 mPa·s
pH	~ 3.2

Application

Rheovis® HS 1332 is an excellent rheology-control agent for water based coatings to increase viscosity in the mid- to high-shear range. The polymer provides the rheology-control effect through extensive swelling of the high-molecular-weight polymer in combination with a hydrophobic component. This leads to superior rheology-build and low spattering, ideal for a broad range of matt to semi-gloss interior and exterior coatings.

Rheovis® HS 1332 is most effective between pH 8 to 10. It offers the following benefits:

- mid to high-shear rheology control
- improved flow
- excellent efficiency
- for paints and plasters

recommended concentrations

1.0 - 3.5% on total formulation.

We recommend to determine the optimum dosage of Rheovis® HS 1332 by laboratory trials to achieve optimum performance.

Rheovis® HS 1332 can be added at any stage of the production process. Afterwards the pH should be checked again and adjusted to 8-10.

Rheovis® HS 1332 can also be mixed into polymer dispersions in the form of an alkaline solution. The solid content of the solution should not be higher than 1% to ensure easy handling. It is recommended to dilute the thickener with water and add alkaline whilst stirring. Check and adjust pH afterwards.

Depending on the application, it can be advisable to use Rheovis® HS 1332 in combination with other Rheovis® thickeners or cellulose derivatives in order to obtain the desired rheological effects.

Contacts worldwide**Asia**

BASF East Asia Regional Headquarters Ltd

45/F, Jardine House

No. 1 Connaught Place

Central Hong Kong

China

formulation-additives-asia@basf.com

North America

BASF Corporation

11501 Steele Creek Road

Charlotte, NC 28273

USA

formulation-additives-nafta@basf.com

Europe

BASF SE

Formulation Additives

67056 Ludwigshafen

Germany

formulation-additives-europe@basf.com

South America

BASF S.A

Rochaverá - Crystal Tower

Av. das Nações Unidas, 14.171

Morumbi - São Paulo-SP

Brazil

formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Rheovis HS 1332.

Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of BASF Group, unless otherwise noted

www.basf.com/formulation-additives