



The Chemical Company

## Softex<sup>®</sup> 1097-A

### Use

Softex 1097-A liquid is 50% calcium stearate dispersion. It is used for anti-tack preparation for rubber industry.

### Specification

Appearance	white emulsion
pH, 2% dispersion	9.0 - 12.0
pH pure	min. 12
Free Alkali	max. 0.2%
Viscosity, 25°C (Brookfield LVT #2,60 rpm)	max. 400 mPas
Solid Content, % (130°C, 1 hr)	49 - 51%
Density, 25°C	1.03 - 1.04 g/cm <sup>3</sup>

### Application

Softex 1097-A is very effective as anti-tack preparation in rubber industry, mold release agent and anti-tack compound for stored slabs, sheets and extruded articles.

Softex 1097-A also reduces cracking in the dry coating, improving printability and preventing dusting at the supercalenders, slitting and printing operations.

### Dosage

The required amount of Softex 1097-A generally lies between 1 - 5 % calculated on the total formulation. Being a liquid it may be mixed directly with the coating at any convenient manufacturing point.

Subject to appropriate storage under the usual storage and temperature conditions, our products are durable for at least 1 year.

**Disclaimer**

The information on product specifications provided herein is only binding to the extent confirmed by BASF in a written Sales Agreement. BASF EXPRESSLY DISCLAIMS ANY RESPONSIBILITY FOR THE SUITABILITY OF THE PRODUCTS FOR ANY SPECIFIC OR PARTICULAR PURPOSES INTENDED BY THE USER. Suggestions for the use and application of the products and guide formulations are given for information purposes only and without commitment. Such suggestions do not release BASF customers from testing the products as to their suitability for the customer's intended processes and purposes. BASF does not assume any liability or risk involved in the use of its products as the conditions of use are beyond its control. The user of the products is solely responsible for compliance with all laws and regulations applying to the use of the products, including intellectual property rights of third parties.

**BASF Care Chemicals - Formulation Technologies**