

# Sovermol<sup>®</sup> 100



## Product description

Sovermol<sup>®</sup> 100 is a polyol used in the manufacturing of polyurethanes

## Key benefits

- Co - polyol (in combination with Sovermol 750 UV-stable)
- Improves glass transition temperature T<sub>g</sub>
- High cross-linking density, hydrophilic
- Improvement of chemical resistance
- Raw materials are listed in EU-Directive 2002/72/EG resp. 2007/19/EC as amended

## Chemical nature

Branched polyether

## Properties

### physical form

Medium viscous, clear liquid

### shelf life

When stored under the usual appropriate storage conditions, the product can be stored for at least 1 year.

### Technical data (no supply specification)

Water content	DIN EN ISO 13267-01	< 0.2%
Acid number	DGF C-V 2	< 1
Hydroxyl number	DGF C-V 17A, B	840 – 920 mgKOH/g
Viscosity (25 °C)	ISO 2555-89	5000 – 7000 mPa·s
Density (25 °C)	DGF C-IV 2B (52)	1.060 – 1.10 g/cm <sup>3</sup>
Color Gardner (930006)		< 1

---

## Application

Sovermol® 100 is recommended for solvent-free coatings of high chemical resistances and hardness. It increases the glass transition temperature also. Sovermol® 100 has normally to be used in combination with other Sovermol® types. As sole polyol it is necessary to homogenize at least 10 minutes to achieve a good compatibility with the isocyanate by increasing the viscosity.

### Mixing Formulation (without filler)

100 g Sovermol® 100
5 g Zeolith paste
213 g Polymer MDI*

\*e.g. Lupranate M 20 S – BASF Polyurethanes

Gel time at 23°C approx. 20 min (30g mass).

### Shore hardness (ISO 868) (storage/room temperature)

	A	D
after 1 day	100	77
after 2 days	100	77
after 3 days	-	-
after 7 days	-	-
after 14 days	100	80
after 28 days	100	80

---

## Technical Data

### Sovermol® 100 in combination with

	Polymer MDI*	MDI (Carbodiimid - modified)**
<b>Shore D hardness RT (ISO 868)</b>		
after 1 day	77	79
after 2 days	77	-
after 3 days	-	-
after 7 days	-	-
after 14 days	80	-
after 28 days	80	88
<b>Mixing ratio</b>	<b>100:213</b>	<b>100:244</b>
<b>Geltime in hours Coesfield</b>	<b>00:20</b>	<b>00:40</b>
<b>Tensile strength in MPa (ISO 527-3 Typ5)</b>	-	-
<b>Elongation in % (ISO 527-3 Typ5)</b>	-	-
<b>Tear resistance in N/mm (ISO 34-1)</b>	-	-
<b>Bending strength in MPa (DIN EN ISO 178)</b>	107	-
<b>Impact resistance in mJ/mm<sup>2</sup> (DIN 53453)</b>	2	-

\* e.g. Lupranat M 20 S, BASF Polyurethanes

\*\* e.g. Supraspec 2010, Fa. Huntsman Polyurethanes

## Registration / Regulatory Information

### Regulatory Status

AICS (Australia)

ENCS/MITI (JP)

EU (EU)

TSCA (USA)

DSL/NDSL (Canada)

PICCS (Philippines)

IECSC (China)

KECI/ECL (Korea)

NZIoC (New Zealand)

Yes

No

### Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

### Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of BASF Group, unless otherwise noted