

Sovermol® 1090

general

Sovermol® 1090 is a polyol used in the manufacturing of polyurethanes

- Low viscosity
- High Hardness – Similar to epoxy systems
- Low reactivity and low exothermic temperature

chemical nature

Branched polyether/polyester

Properties

physical form

Yellow, low viscous, clear polyol

shelf life

When stored under the usual appropriate storage conditions, the product can be stored for at least 1 year.

typical properties (no supply specification)

Water content (ISO 4317 - 93003001)	<= 0.2%
Acid number (DGF C-V 2)	<= 2.0 mg KOH/g
Hydroxyl number (DGF C-V 17A,B)	290 – 310 mg KOH/g
Viscosity (dynamic) (25 °C) (ISO 2555)	700 – 1200 mPa·s
Density (25 °C) (DGF C-IV 2)	1.02 – 1.03 g/cm ³

Application

In combination with Polymer MDI Sovermol® 1090 can be used for the production of 2-pack PU coating, casting materials and also 2-pack adhesives.

Application example (without filler)

100 g Sovermol® 1090
5 g Zeolith paste
73 g Polymer MDI*

*e.g. Lupranate M 20 S – BASF Polyurethanes

Gel time at 23°C approx. 91 min (30g mass).

Shore hardness (ISO 868) (storage/room temperature)

	A	D
after 1 day	-	71
after 2 days	-	80
after 3 days	-	85
after 7 days	-	86
after 14 days	-	87
after 28 days	-	87

Technical Data**Sovermol® 1090 in combination with****Polymer MDI*****Shore D hardness RT (ISO 868)**

after 1 day	71
after 2 days	80
after 3 days	85
after 7 days	86
after 14 days	87
after 28 days	87

Mixing ratio 100:73

Geltime in hours Coesfield 01:31

Tensile strength in MPa 34
(ISO 527-3 Typ5))

Elongation in % 4
(ISO 527-3 Typ5)

Tear resistance in N/mm 16
(ISO 34-1)

Bending strength in MPa -
(DIN EN ISO 178)

Impact resistance in mJ/mm² -
(DIN 53453)

* e.g. Lupranat M 20 S, BASF Polyurethanes

Registration / Regulatory Information

Approvals**Regulatory Status**

AICS (Australia)
ENCS (JP)
EINECS (EU)
TSCA (USA)
DSL (Canada)
PICCS (Philippines)
IECSC (China)
KECL (Korea)
NZIoC (New Zealand)

<input type="radio"/>	
<input type="radio"/>	
<input checked="" type="radio"/>	
<input type="radio"/>	
<input type="radio"/>	
<input type="radio"/>	
<input type="radio"/>	
<input type="radio"/>	
<input type="radio"/>	
<input type="radio"/>	
<input checked="" type="radio"/>	Yes
<input type="radio"/>	No

Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of BASF Group, unless otherwise noted