

Technical Data Sheet

CG-172

Description

Chemical Name Vinyltris(2-methoxyethoxy)silane

Molecular Formula C₁₁H₂₄O₆Si

Structural Formula

şi-0_-

Molecular Weight 280.4
CAS No. 1067-53-4

Physical Properties

Physical Form Transparent liquid
Color Clear, colorless

Assay, % ≥98

Specific Gravity at 25°C, g/cm³ 1.030-1.035

Boiling Point, °C 285

Refractive Index, N_D²⁰ 1.4275-1.4295

Flash Point, Closed Cup, °C 92

Applications

This product can be applied to polythene and copolymer with various complex shapes in all densities, and also can be used in the aspects of large processing technique tolerance and composites filler etc. It can be grafted to the main chain of the polymer to modify polyethylene and other polymers, and then the side chain would get the Si-OCH₂CCH₃ group, as the active point of water crosslink. The grafted polyethylene can be made into mature products, such as cable shields, insulations, tubes or other extruding and pressing products, EPDM rubber, etc. Also can be used in the glass fiber industry.

Packaging and Storage

Be packed in 200KG drums, IBC and ISO Tank.

Be sealed and stored in cool and well ventilated place. Away from fire and water.

DISCLAIMER

The information provided herein was believed by Jiangxi Chenguang New Materials Co., Ltd. to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for user's intended application or use. All products supplied by Chenguang are subject to Chenguang's standard terms and conditions of sale. CHENGUANG MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY CHENGUANG, except that the product shall conform to Chenguang's specifications. Nothing contained herein constitutes an offer for the sale of any product. For more information, please visit our website at: www.cqsilane.com