

Dehydol® LT 5


® = Registered trademark of BASF
in many countries.

Nonionic surfactants for the detergent and cleaner industry

Chemical character

The Dehydol® LT types are nonionic surfactants. They are alkyl polyethylene glycol ethers made from a C₁₂-C₁₈-alcohol and ethylene oxide.

They conform to the following formula:



R = C₁₂-C₁₈ Alkyl

Dehydol® LT 5: x = 5

The numeric code in the product name indicates in general the degree of ethoxilation.

PRD-No.*

30528562

* BASF's commercial product numbers.

Properties

Dehydol® LT 5 is a cloudy liquid at room temperature and tends to form sediment. Dehydol® LT 5 becomes clear liquid at 40 °C.

Dehydol®	Unit	
Physical form (23 °C)	liquid	
Degree of ethoxilation	mol	approx. 5
Concentration	%	approx. 100
Cloud points (EN 1890)*		
Method D	°C	approx. 73
Method E	°C	approx. 70
Molar mass (from OH number)	g/mol	approx. 420
pH value (EN 1262, solution A)**		approx. 7
Density (DIN 51757, 23 °C)	g/cm ³	approx. 0.96
Dropping point (DIN 51801)	°C	approx. 13
Congealing point (ISO 2207)	°C	approx. 12
Viscosity (EN 12092, 23 °C, Brookfield, 60 rpm)	mPa·s	approx. 90
Hydroxyl number (DIN 53240)	mg KOH/g	approx. 134
HLB value		approx. 10.5
Flash point (ISO 2592)	°C	approx. 190
Wetting (EN 1772, distilled water, 23 °C, 2 g Soda ash/l)		
0.5 g/l	s	approx. 120
1.0 g/l	s	approx. 55
2.0 g/l	s	approx. 25
Foam volume (EN 12728, 40 °C, 2 g/l water at a hard- ness of 1.8 mmol Ca- ions/l, after 30 s)	cm ³	approx. 50
Surface tension (EN 14370, 1 g/l in distilled water, 23 °C)***	mN/m	approx. 28

* Cloud point EN 1890:

Method A: 1 g of surfactant + 100 g of dist. Water

Method B: 1 g of surfactant + 100 g of NaCl solution (c = 50 g/l)

Method C: 1 g of surfactant + 100 g of NaCl solution (c = 100 g/l)

Method D: 5 g of surfactant + 45 g of butyldiglycol solution (c = 250 g/l)

Method E: 5 g of surfactant + 25 g of butyldiglycol solution (c = 250 g/l)

** The pH of the Dehydol® LT types can decrease during storage, but this does not have any effect on their performance.

*** Applying Harkins-Jordan correction.

The above information is correct at the time of going to press. It does not necessarily form part of the product specification. A detailed product specification is available from your local BASF representative.

Solubility

Details on the solubility of Dehydol® LT 5 in various solvents are given in the table below.

Solubility of the Dehydol® LT 5 (10% at 23 °C)

	Dehydol® LT 5
Distilled water	–
Potable water (2.7 mmol Ca ²⁺ -Ions/l)	–
Caustic soda (5%)	–
Hydrochloric acid (5%)	–
Salt solution (5%)	–
Solvent naphtha	+
Ethanol, Isopropanol	+
Aromatic hydrocarbons	+

+ = *clear solution*

± = *sparingly soluble (insoluble sediment)*

– = *insoluble (phase separation)*

○ = *forms an opaque soluble, homogeneous emulsion*

Viscosity

The relationship between viscosity and temperature is always an important point to consider when Dehydol® LT 5 is stored or shipped. This is shown in the following table (mPa·s, Brookfield LVT):

Viscosity at °C	Dehydol® LT 5
0	Solid
10	>10 ⁵
20	170
23	90
30	50
40	25
50	<20
60	<20

We would recommend the preparation of 10 – 25% stock solutions of Dehydol® LT 5 if it is to be used in the form of very dilute solutions, or if it is to be added to other solutions. This makes it very much easier to dilute it later on.

Dehydol® LT 5 can form fairly stiff gels at certain concentrations when water is added. The figures below were measured using a Brookfield-Viscosimeter at 23 °C and 60 rpm.

The viscosity of Dehydol® LT 5 at 23 °C as a function of concentration in water (all values in mPa·s)

Water addition in %	Dehydol® LT 5
0	90
10	190
20	>10 ⁵
30	>10 ⁵
40	45000
50	2000
60	400
70	950
80	900
90	300

The numbers reported have to be regarded as maximum values; the values measured immediately after mixing will be lower than the numbers reported.

Storage

- Dehydol® LT 5 should be stored indoors in a dry place. Storage rooms must not be overheated (see flash point).
- Dehydol® LT 5 is hygroscopic due to its good solubility in water, with the result that it may absorb moisture very quickly. Drums must be resealed each time they are opened.
- The storage temperature should not be allowed to fall substantially below 20 °C. The congealing point of Dehydol® LT 5 also need to be taken into account.
- Dehydol® LT 5 is a cloudy liquid and tend to form sediment, it becomes clear liquid at 40 °C.
- Liquid that has solidified or that shows signs of sedimentation should be heated to 50 – 70 °C and homogenized before it is processed. Please mix sufficiently prior to use.
- Drums that have solidified or that have begun to precipitate should be reconstituted by gentle heating, preferably in a heating cabinet. The temperature must not be allowed to exceed 70 °C. Please mix sufficiently prior to use. This also applies if drums are heated by external electrical elements. Internal electrical elements should not be used because of the localized anomalies in temperature that they cause.
- Dehydol® LT 5 must be blanketed with nitrogen if they are stored in heated tanks (at 50 – 60 °C) to prevent it from coming into contact with air. Constant, gentle stirring helps to prevent it being discolored as a result of prolonged contact with electrical elements or external heating coils.

Materials

The following materials can be used for tanks and drums:

- AISI 321 stainless steel (X6CrNiTi1810)
- AISI 316 Ti stainless steel (X6CrNiMoTi17122)

Shelf life

Provided it is stored properly and drums are kept tightly sealed, Dehydol® LT 5 have a shelf life of at least two years in its original packaging.

Safety

We know of no ill effects that could have resulted from using Dehydol® LT 5 for the purpose for which it is intended and from processing it in accordance with current practices.

According to the experience that we have gained over many years and other information at our disposal, Dehydol® LT 5 does not exert harmful effects on health, provided it is used properly, due attention is given to the precautions necessary for handling chemicals, and the information and advice given in our Safety Data Sheets are observed.

Please refer to the latest Safety Data Sheet for detailed information on product safety.

Note

This document, or any answers or information provided herein by BASF, does not constitute a legally binding obligation of BASF. While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. It does not relieve our customers from the obligation to perform a full inspection of the products upon delivery or any other obligation. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE.

May 2013