
Technical Information

January 2017
Supersedes issue dated May 2015

09_150102e-02/Page 1 of 3
Last change WF-No. 10684

® = Registered trademark of BASF
in many countries.

Sokalan® CP 9

Maleic acid/Olefin copolymer, Na-Salt.

Dispersing agent for organic and inorganic solids, particularly for aqueous media and mixtures of water and organic solvents.

Chemical nature

Aqueous solution of a copolymer based on Maleic acid and Olefin, Na-Salt.

PRD-No.*

30042823

* BASF's commercial product numbers.

Appearance

Sokalan® CP 9 is a clear, rarely slightly cloudy, colorless till yellowish liquid at room temperature and tends to form sediment in the coldness.

Handling and Storage**Handling ONLY packaged goods**

- Sokalan® CP 9 should be stored in a dry place in its original sealed packaging.
- Sokalan® CP 9 can slightly separate during the storage time. The product must be homogenized before it is processed. It must be mixed sufficiently prior to use.
- The storage temperature must be between min. 0 °C and max. +45 °C. Storage temperatures above +30 °C will cause an increase of the color number. At low temperatures (approx. +5 °C) Sokalan® CP 9 forms crystals and becomes solid. Drums or IBCs containing solidified product or liquid that have begun to precipitate or separate should be reconstituted by gentle heating, preferably in a heating cabinet. Warming up to max. + 30 °C allows the product to become liquid again. It must be mixed sufficiently prior to use. This also applies if drums are heated by external electrical elements. Internal electrical elements should not be used because of the localized anomalies in temperature that they can cause. Sokalan® CP 9 is frost sensitive! Storage temperatures below 0 °C destroy the product properties. This is an irreversible process.
- Sokalan® CP 9 must be protected from sunlight and high temperatures to avoid discoloration and the formation of surface films.
- Sokalan® CP 9 must be blanketed with nitrogen if it is stored to prevent air contact. Air contact can cause discoloration.
- Please refer to the latest Safety Data Sheet for detailed information on product safety.

Handling ONLY bulk containers

- The storage temperature for bulk product must be between min. 0 °C and max. +45 °C. Storage temperatures above +30 °C cause an increase of the color number. At low temperatures (approx. < +5 °C) Sokalan® CP 9 forms crystals and becomes solid.
- Sokalan® CP 9 can slightly separate during the storage time. The product must be homogenized before it is processed. It must be mixed sufficiently prior to use. Sokalan® CP 9 is frost sensitive! Storage temperatures below 0 °C destroy the product properties. This is an irreversible process.
- Sokalan® CP 9 must be protected from high temperatures (> +40 °C) to avoid discoloration and the formation of surface films.
- Sokalan® CP 9 must be blanketed with nitrogen if it is stored in heated tanks (at max. +40 °C) to prevent air contact. Air contact can cause discoloration. Constant, gentle stirring helps to prevent it being discolored as a result of prolonged contact with electrical elements or external heating coils.
- Please refer to the latest Safety Data Sheet for detailed information on product safety.

Shelf life

Sokalan® CP 9 has a shelf life of at least 24 months in its original packaging.

Materials

The following materials can be used for tanks and drums:

- a) Stainless steel 1.4541 – AISI 321 stainless steel (X6 CrNiTi 1810)
- b) Stainless steel 1.4571 – AISI 316 Ti stainless steel (X6 CrNiMoTi 17122)
- c) Stainless steel 1.4306 – AISI 304 L stainless steel (X2 CrNi 1911)
- d) HDPE – high density polyethylene
- e) LDPE – low density polyethylene

Properties

Some physical properties are listed in the table below. These are typical values only and not all of them are monitored on a regular basis. They are correct at the time of publication and do not necessarily form part of the product specification. A detailed product specification is available on request or via BASF's WorldAccount: <https://worldaccount.basf.com> (registered access).

Sokalan® CP 9	Unit	Value
Physical form (25 °C)		liquid
Concentration (dry content) (ISO 3251, 3 g, 120 °C, 30 min.)	%	approx. 25
pH value (DIN 19268, 25 °C, as is)		approx. 11
Iodine color (EN 1557, 25 °C, as is)		approx. 2
K value (ISO 1628-1, 1.0% dry substance in dist. water)		approx. 35
Viscosity (EN 12092, Brookfield, 25 °C, as is, Spindle 1, 100 rpm)	mPa·s	approx. 50
Density (DIN 51757, method 3) 25 °C 40 °C	g/cm ³ g/cm ³	approx. 1.12 approx. 1.11
Water content (=100%-Concentration (dry content))	%	approx. 75
Solubility (visual, 23 °C, 10% dry substance in dist. water)		clear to slightly turbid
Pour point (ISO 3016)	°C	approx. -2
Residual Na-maleate (calculated as Maleic acid, HPLC BASF method)	%	approx. 0.3

Safety

We are not aware of any ill effect that can result from using Sokalan® CP 9 for the purpose for which it is intended and from processing it in accordance with current practices.

According to the experience that we have gained over many years and other information at our disposal, Sokalan® CP 9 does not exert harmful effects on health, provided it is used properly, due attention is given to the precautions necessary for handling chemicals, and the information and advice given in our Safety Data Sheets are observed.

Disclaimer

This document, or any answers or information provided herein by BASF, does not constitute a legally binding obligation of BASF. While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. It does not relieve our customers from the obligation to perform a full inspection of the products upon delivery or any other obligation. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE.

January 2017