

Tinuvin[®] 5050

Product Description

Tinuvin 5050 is a solvent-free, liquid blend of a 2-(2-hydroxyphenyl)-benzotriazole UV absorber (UVA) and a basic hindered amine light stabilizer (HALS) designed to fulfill the high cost/performance and durability requirements of exterior solventborne industrial and decorative coatings.

Key Features & Benefits

- Synergistic blend of UVA/HALS for solvent based systems
- Provides protection of coatings against cracking, loss of gloss, and color change
- Recommended for non-acid catalyzed systems

Chemical Composition

Blend of 2-(2-hydroxyphenyl)-benzotriazole UVA and a basic HALS

Properties


Typical Properties

Appearance		viscous amber liquid
Dynamic Viscosity at 25 °C	cps	10,000
Density at 20 °C	g/cm ³	1.034

Miscibility Tinuvin 5050 is miscible to more than 50% with most commonly used paint solvents. Water solubility is less than 0.01%.


These typical values should not be interpreted as specifications.

UV Absorbance Spectrum (40 mg/l in chloroform, cell thickness = 1 cm)



UV Transmission Spectrum

(The theoretical concentration of the UVA in an applied 40 µm clear coat was calculated as a function of the concentration in chloroform ($d = 1.48 \text{ g/cm}^3$) with the help of the Lambert-Beer law)



Line one: 0.003 % Tinuvin 5050 corresponds to 0.68% active UVA in a 40 µm film
Line two: 0.005 % Tinuvin 5050 corresponds to 1.35% active UVA in a 40 µm film
Line three: 0.014 % Tinuvin 5050 corresponds to 3.38% active UVA in a 40 µm film

Applications

Tinuvin 5050 is a versatile light stabilizer that can be used in a variety of coatings systems such as:

- Wood stains and varnishes, wood care products, waxes
- Architectural coatings (roof tiles, walls, floor coatings)
- General Industrial Paints
- Heavy duty maintenance and marine coatings
- Glass and ceramic coatings (architectural glazing, packaging)
- Adhesives and bonding layers

Its use is especially recommended for clear and light pigmented systems like:

- Thermoplastics (Acrylics, Vinylics)
- 1 and 2 K-PUR (Acrylic/NCO, PES/NCO)

The broad UV absorbance of Tinuvin 5050 makes it suitable for a wide range of coatings for wood, plastics and metal. The synergistic combination imparts superior coating protection against gloss reduction, cracking, blistering, delamination, and color change and provides full substrate protection.

Recommended concentrations

The amount of Tinuvin 5050 required for optimum performance should be determined in laboratory trials covering a concentration range.

The dry film thicknesses (DFT) directly affects the amount of UVA needed. The following recommended concentrations are to achieve proper stabilization for given DFT (light stabilizers % is indicated on total formulation):

10 µm – 20 µm:	8.0 % – 4.0 %
20 µm – 40 µm:	4.0 % – 2.0 %
40 µm – 80 µm:	2.0 % – 1.0 %

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measure described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care, and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Tinuvin 5050.

Storage

Please refer to the "Handling and Storage of Polymer Dispersions" brochure.

Important

The descriptions, designs, and data contained herein are presented for your guidance only. Because there are many factors under your control which may affect processing or application/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, and data furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk.

Tinuvin is a registered trademark of BASF Group.

© BASF Corporation, 2019



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico. For more information on Responsible Care® go to:
U.S.: www.basf.us/responsiblecare_usa
Canada: www.basf.us/responsiblecare_canada
México: www.basf.us/responsiblecare_mexico

BASF Corporation
Dispersions and Resins
11501 Steele Creek Road
Charlotte, North Carolina 28273
Phone: (800) 251 – 0612
Email: CustCare-Charlotte@basf.com
Email: edtech-info@basf.com
www.basf.us/dpsolutions